

Quality	X17CrNi16-2
According to Standard	EN 10088-3:2005 (E)
Number	1.4057

Comparable Standards	EN	W.N.	AISI
	X17CrNi16-2	1.4057	431

Chemical Analysis	C %	Si % max	Mn %	P% max	S%	Cr %
	0.12 - 0.22	1.00	≤ 1.50	0.04	≤ 0.030 ^b	15.0 - 17.0
	Cu	Mo %	Nb	Ni %	Others	
	—	—	—	1.50 - 2.50	—	

Hot Work and Heat Treatment Temperatures

Heat Treatment Symbol	Hot Forming		Annealing		Quenching		Tempering Temperature °C
	Temperature °C	Type of cooling	Temperature °C	Type of cooling	Temperature °C	Type of cooling	
+A ^c	1100 to 800	slow cooling	680 to 800	furn.,air	—	—	—
+QT 800 ^d	1100 to 800	slow cooling	—	—	950 to 1050	oil, air	750 to 800 + 650 to 700 ^d
+QT 900	1101 to 800	slow cooling	—	—	950 to 1050	oil, air	600 to 650

Mechanical Properties at Room Temperature

Heat Treatment Condition	Ø mm.	Hardness HB ^c max	Rp0,2 ^d min. N/mm2	Rm ^d N/mm2	A ^d min. %	KV min. J
+A	—	295	—	max 950	—	—
+QT 800	≤ 60	—	600	800 to 950	14	25
	60 < t ≤ 160	—			12	20
+QT 900	≤ 60	—	700	900 to 1050	12	20
	60 < t ≤ 160	—			10	15