

Quality S355J0 (Fe 510 C)



According to Standard EN 10025 - 2 : 2004

Number 1.0553

Comparable Standards	German DIN	France AFNOR	Spain UNE	China GB	U.K. B.S.	Russia GOST	USA AISI - SAE	Japan JIS
----------------------	------------	--------------	-----------	----------	-----------	-------------	----------------	-----------

	St52-3U	E36-3			50C	St4sp	A441	SCCC 3
--	---------	-------	--	--	-----	-------	------	--------

Chemical Analysis	C% max	Si% max	Mn% max	P% max	S% max	N% max	Cu% max	Cast & Product Analysis
-------------------	--------	---------	---------	--------	--------	--------	---------	-------------------------

	0.023	0.60	1.70	0.040	0.030 - 0.040	0.014	0.45	
--	-------	------	------	-------	---------------	-------	------	--

Hot Work and Heat Treatment Temperatures

Temperature °C

Hot - Forming	Supply State +U	Soft Annealing +A	Isothermal Annealing +I	Normalising & Tempering	Quenching & Tempering QT	Stress-relieving +SR
1150 - 850	natural state	650 - 700 air		880 - 900 air	860 - 900 water	50° under the temperature of tempering
				550 - 660 air	550 - 660 air	

Mechanical Properties at Room Temperature

Minimum Yield Strength R^{eH}
Mpa
Nominal Thickness mm

	≤ 16	> 16	> 40	> 63	> 80	> 100	> 150	> 200
		≤ 40	≤ 63	≤ 80	≤ 100	≤ 150	≤ 200	≤ 250
	275	265	255	245	235	225	215	205

Tensile Strength R
Mpa
Nominal Thickness mm

	< 3	> 3	> 100	> 150
		≤ 100	≤ 150	≤ 250
	430 to 580	410 to 560	400 to 540	380 to 540

Minimum percentage elongation after fracture %

	L = 80 mm. Normal thickness mm				L = 5.65 √S ₀ . Nominal thickness mm					
	≤ 1	> 1	> 1.5	> 2	> 2.5	> 3	> 40	> 63	> 100	> 150
		≤ 1.5	≤ 2	≤ 2.5	< 3	≤ 40	≤ 63	≤ 100	≤ 150	≤ 250
l	15	16	17	18	19	23	22	21	19	18
t	13	14	15	16	17	21	20	19	19	18

